

ADVA[®] Cast 530

High-range water-reducing admixture -- ASTM C494 Type A and F and ASTM C1017 Type I

Product Description

ADVA[®] Cast 530 is a high efficiency polycarboxylate-based superplasticizer. ADVA[®] Cast 530 has been formulated to impart extreme workability without segregation to concrete and to achieve high early compressive strength as required by the precast industry. ADVA[®] Cast 530 is optimized for the production of Self-Consolidating Concrete (SCC) in precast applications. ADVA[®] Cast 530 is formulated to comply with ASTM C494 as a Type A and F and ASTM C1017 Type I.

ADVA[®] Cast 530 is supplied as a ready-to-use brown liquid, one gallon weighs approximately 8.90 lbs (one liter weighs approximately 1.07 kg). ADVA[®] Cast 530 contains no intentionally added chlorides.

Product Advantages

- Imparts excellent stability to high flow concrete
- Excellent surface finish

Uses

ADVA[®] Cast 530 is recommended for use in precast and prestressed production in conventional and Self-Consolidating Concrete applications.

Conventional Concrete Applications of ADVA[®] Cast 530:

- Can produce concrete with extremely high levels of workability without segregation.
- May be used to produce concrete with very low water/cement ratios while maintaining normal levels of workability.
- Ideal for use in precast and prestressed applications where concrete needs to achieve high early strength along with high levels of workability.
- Provides superior concrete surface finish characteristics with reduced bugholing.

Self-Consolidating Concrete Applications:

SCC produced with ADVA[®] Cast 530 has unique advantages over conventional flowing concrete.

- **Self placement** - vibration can be eliminated because SCC is highly flowable and will change shape under its own weight to self level and self consolidate within formwork.
- **No segregation** - SCC is a flowable yet highly cohesive material that will not segregate and has significantly reduced bleeding.
- **No blocking** - SCC can pass freely through narrow openings and congested reinforcement without aggregate "blocking" behind obstructions that stop the flow of concrete.

Addition Rates

ADVA® Cast 530 is an easy to dispense liquid admixture. Dosage rates can be adjusted to meet a wide spectrum of concrete performance requirements. Addition rates for ADVA® Cast 530 can vary with the type of application, but will normally range from 3 to 10 fl oz/100 lbs (200 to 650 mL/100 kg) of cement. Should conditions require using more than the recommended addition rate, please consult your GCP representative.

For SCC applications, pre-placement testing is recommended to determine the optimum admixture addition rate and mix design. Factors that influence optimum addition rate include other concrete mix components, aggregate gradations, form geometry and reinforcement configurations. Please consult your local GCP Applied Technologies representative for assistance with developing mix designs for Self-Consolidating Concrete.

Compatibility with Other Admixtures and Batch Sequencing

ADVA® Cast 530 is compatible with most GCP admixtures as long as they are added separately to the concrete mix. However, ADVA® products are not recommended for use in concrete containing naphthalene-based admixtures including DARACEM® 19 and DARACEM® 100 and melamine-based admixtures including DARACEM® 65. In general, it is recommended that ADVA® Cast 530 be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see GCP Technical Bulletin TB-0110, *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations.

Pretesting of the concrete mix should be performed before use and as conditions and materials change in order to assure compatibility with other admixtures, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air-entraining agent (such as DARAVAIR® or DAREX® product lines) is recommended to provide suitable air void parameters for freeze-thaw resistance. Please consult your GCP Applied Technologies representative for guidance.

Packaging & Handling

ADVA® Cast 530 is available in bulk, delivered by metered trucks, in totes and drums. ADVA® Cast 530 will freeze at approximately 32°F (0°C) but will return to full functionality after thawing and thorough mechanical agitation.

Dispensing Equipment

A complete line of accurate, automatic dispensing equipment is available.

gcpat.com | North America Customer Service: 1 877-4AD-MIX1 (1 877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

ADVA, DAREX, DARACEM, and DARAVAIR are registered trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies, Inc.

All rights reserved. GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140, USA

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2018-08-24

gcpat.com/solutions/products/adva-cast-high-range-water-reducers/adva-cast-530